



860JF

PRODUCT DESCRIPTION

Simiron 860JF is a fast-set, semi-rigid polyurea used for filling control and construction joints in concrete floors. This high-performance system is mixed and applied via a dual cartridge mechanism or plural mixer. The 100% solids, VOC-free system provides excellent UV resistance, is moisture insensitive, and offers a large shave-time window.

860JF supports and protects joint edges from heavy loads and wheel traffic, reducing spalling of the joint edges.

FEATURES & BENEFITS

- Fast setting formula
- Protects joints from debris and damages from heavy traffic
- Excellent UV Resistance
- 100% Solids system free of VOC's
- Self-leveling, low viscosity system
- Wide application and service temperature range, including freezer applications
- Low temperature applications as low as -25°F (-32°C)
- Moisture insensitive
- Acceptable in USDA inspected facilities
- No foaming or bubbling in damp joints
- Excellent performance properties
- Large shave-time window
- Complies with ACI 302 regarding control and construction joint fillers

TECHNICAL DATA

PHYSICAL DATA		COLOR	ITEM NUMBER	CURE TIMES @ 72F (22C), 50% RH	
Dual Component Cartridges 22 oz. (600mL)		Concrete Gray	40002879	Tack Free	12 - 15 minutes
Tintable 10 Gallon (37.9L) Kits		Neutral	28863227	Shave Time	30 minutes to 4 hours
Tintable Base: 5 US Gal (18.9 L)		Neutral	40002893	Light Traffic	1 hour
Activator: 5 US Gal (18.9 L)		Amber/Brown	40002886	Heavy Traffic	2 hours

TECHNICAL DATA (CONT.)

PHYSICAL DATA	
Components	2 (Base + Activator)
Color	Haze Gray
Solids Content	100%
Mix Ratio (by volume)	1: 1
Gel Time 100 Gram mass @ 72°F (22°C)	3 - 8 seconds
Viscosity	Base - 900 cPs, Activator - 1200 cPs
VOC (EPA Method 24)	10 g/L

COVERAGE

The following chart provides approximate coverage estimates in linear ft. /gal (m/L).

JOINT WIDTH	1.5 " (38 MM) DEPTH	2 " (51 MM) DEPTH	2.5 " (63 MM) DEPTH
1/8" (3.2 mm)	103' (8.2 m)	77' (6.1 m)	62' (4.9 m)
3/16" (4.8 mm)	68' (5.4 m)	51' (4.1 m)	41' (3.3 m)
1/4" (6.4 mm)	51' (4.1 m)	39' (3.1 m)	31' (2.5 m)
3/8" (9.5 mm)	34' (2.7 m)	26' (2.1 m)	21' (1.7 m)

PHYSICAL PERFORMANCE PROPERTIES

PHYSICAL PROPERTIES	TEST METHOD	RESULTS
Adhesion to Concrete	ASTM D4541	275 psi (1.9 MPa)
Elongation	ASTM D412	242%
Shore A Hardness	ASTM D2240	91
Tensile Strength	ASTM D412	1642 psi (11.3 MPa)

SURFACE PREPARATION

Concrete should be a minimum of 28 days old. Joints must be clean, dry and free of all contaminants such as dirt, dust, grease, paint, oil and other foreign materials. Preferred methods of joint cleaning include using a dustless concrete saw with a diamond blade or sandblasting. Remove all residues and debris using a HEPA filtered vacuum cleaner or oil-free air compressor. Joints should be clean and dry before application to ensure best adhesion to concrete.

SAFETY AND TECHNICAL

Refer to the SDS sheet before use. Safety precautions must be strictly followed during storage, handling, and use. Personal protective equipment (PPE) should be worn at all times. PPE will include (but is not limited to): Safety glasses with side shields and high quality nitrile gloves. To acquire additional information or technical and safety data, please visit: www.simiron.com

TEMPERATURE

Air	-25° - 120°F	-32° - 49°C
Surface	-25° - 120°F	-32° - 49°C
Material	60° - 85°F	16° - 29°C

Higher temperatures will shorten work time.

APPLICATION EQUIPMENT

Assemble all equipment. Equipment will include (but is not limited to)

- 1:1 Ratio Dual Component Manual or Air Gun
- 1:1 Ratio Dual-feed power dispensing equipment

APPLICATION PROCEDURE

Simiron 860JF mix ratio is 1 part Base to 1 part Activator by volume. Material in pails should be thoroughly mixed before use. Mix at low speed using a power drill and paddle to ensure each part is thoroughly premixed before mixing the base and activator together using a plural mixer, do not whip air into material while mixing. Prefilled cartridges should be shaken for two minutes to ensure material is thoroughly mixed before use. Follow specific instructions on cartridge before use.

DISPENSING AND FILLING

Use a ½" diameter static mixer with 30 or 32 elements for dispensing and proper mixing. Simiron 860 JF must be installed in the joint to full depth. Joints should be slightly overfilled so that they can be shaved flush with surrounding concrete joint edges. Take care to not trap air bubbles when filling the joints.

SHAVING

Shaving Simiron JF 860 can be done as soon as 30 minutes, depending on surface and air temperature conditions. Be sure to always use a sharp blade when shaving joints flush to ensure a smooth finish.



860JF

CLEAN UP & DISPOSAL

Simiron 860JF can be cleaned up using NMP, xylene, MEK or other mild solvents; follow all solvent manufacturers' safety instructions.

LIMITED WARRANTY

SIMIRON warrants this product to be free from defect in the material that affects its performance for a period of one year (from date of purchase). SIMIRON will replace at no charge the quantity of the Coating that SIMIRON determines has failed to perform, as the sole and exclusive remedy for any breach of this warranty and/or any other defect or failure of the coating. Proof of purchase is required. Cost of labor for application of any product specifically is excluded. Warranty is void if Simiron products are mixed with or used in conjunction with materials that are substituted for Simiron products. Warranty is nontransferable

SHELF LIFE AND STORAGE

12 months from date of manufacture when stored indoors in the original unopened container at 60°F – 85°F (16°C – 29°C) in a dry location with humidity below 65%

⚠ Do not allow materials to freeze.

TECHNICAL ASSISTANCE



Information is available by calling SIMIRON
Toll Free: 1.866.515.8775 / +1.248.686.3600



CORPORATE OFFICE:

Simiron Inc
3000 Research Drive
Rochester Hills, MI 48309-3580
USA
(248) 686-3600 / (866) 515-8775

PRODUCT DATA SHEET: 03/31/2025

Disclaimer: All information provided by Simiron, Inc. concerning Simiron products, including but not limited to, any recommendations and advice relating to the application and use of Simiron products, is given in good faith based on Simiron's current experience and knowledge of its products when properly stored, handled, and applied under normal conditions in accordance with Simiron's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual conditions and other factors outside of Simiron's control are such that Simiron assumes no liability for the provision of such information, advice, recommendations or instructions related to its products. The uses of Simiron product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s).

Simiron reserves the right to change the properties of its products without notice. All Simiron product(s) are subject to its current terms and conditions of sale which are available by calling (866) 515-8775.