



Technical Data Sheet

Product	KKR1x SheenSeries		
Description	Pigmented polyurethane top-coats		
Guarantee, Regulation, Certification	EN71/3 (2013)		
Color	Pigmentable white		
Chemical-physical Properties			
CODE	Density (Kg/l)	Density (lb/US gal)	Solid content %
KKR00	1,225 ± 0,030	10,2 ± 0,3	62,8 ± 2
KKR01	1,164 ± 0,030	9,7 ± 0,3	60,2 ± 2
LKR17373	1,282 ± 0,030	10,7 ± 0,3	65,8 ± 2
KKR1	1,296 ± 0,030	10,8 ± 0,3	65,9 ± 2
KKR3	1,256 ± 0,030	10,5 ± 0,3	66,5 ± 2
KKR2	1,288 ± 0,030	10,7 ± 0,3	66,6 ± 2
(series average values)	Viscosity (EN ISO 2431) ISO 6 cup		90 ± 5
USAGE INDICATIONS			
Additional products		Quantities	
Hardener	LNB77	In weight w/w %	50
		In volume v/v %	63,6
	Solid content %	23,4 ± 2	
Thinner	LZC8643	In weight w/w %	30
		In volume v/v %	43
READY TO USE PRODUCT PROPERTIES (AVERAGE)			
	Solid content 1st + 2nd component (%)	49,7 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	3 h	
	Viscosity (Ford 4 cup)	20 ± 2	
Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)	
		applied micron: 140	
		Wet Mils: 5,5	
	KKR00	Sheen	80 ± 5
	KKR01	Sheen	50 ± 3
	LKR17373	Sheen	40 ± 3
	KKR1	Sheen	20 ± 2
	KKR3	Sheen	15 ± 1
KKR2	Sheen	10 ± 1	



Application		Quantities			
Application	Robot spray	gr/m ² min-max: 130 - 160			
		Wet Mills min-max 4,8 - 5,9			
	Hand spray	gr/m ² min-max: 130 - 160			
		Wet Mills min-max 4,8 - 5,9			
PRODUCT PROPERTIES AFTER APPLICATION					
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		12 h		
	Dust free		10 min		
	Touch dry		30 min		
	Hard dry		12 h		
	Hot air drying		(Time and temperature according to the drying system in use)		
Additional products		Quantities			
Hardener	LNB20	In weight w/w %		50	
		In volume v/v %		62,8	
	Solid content %		25,0 ± 2		
Thinner	LZC8643	In weight w/w %		30	
		In volume v/v %		43	
READY TO USE PRODUCT PROPERTIES (AVERAGE)					
	Solid content 1st + 2nd component (%)		50,2 ± 2		
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)		3 h		
	Viscosity (Ford 4 cup)		20 ± 2		
Code/Sheen	CODE		Sheen level EN ISO 2813 (angle measurement 60°)		
			applied micron: 140		
			Wet Mills: 5,5		
	KKR00		Sheen 85 ± 5		
	KKR01		Sheen 54 ± 3		
	LKR17373		Sheen 40 ± 3		
	KKR1		Sheen 22 ± 2		
	KKR3		Sheen 17 ± 1		
	KKR2		Sheen 12 ± 1		
Application		Quantities			
Application	Robot spray	gr/m ² min-max: 130 - 160			
		Wet Mills min-max 4,8 - 5,9			
	Hand spray	gr/m ² min-max: 130 - 160			
		Wet Mills min-max 4,8 - 5,9			



PRODUCT PROPERTIES AFTER APPLICATION				
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	10 h		
	Dust free	10 min		
	Touch dry	30 min		
	Hard dry	10 h		
	Hot air drying	(Time and temperature according to the drying system in use)		
Additional products		Quantities		
Properties	Excellent Yellowing resistance			
Hardener	LNB190	In weight w/w %	50	
		In volume v/v %	65,1	
	Solid content %	26,2 ± 2		
Thinner	LZC8643	In weight w/w %	30	
		In volume v/v %	43	
	Solid content 1st + 2nd component (%)	50,6 ± 2		
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	3 h		
	Viscosity (Ford 4 cup)	18 ± 2		
Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)		
		applied micron: 140		
		Wet Mils: 5,5		
	KKR00	Sheen	82 ± 5	
	KKR01	Sheen	52 ± 3	
	LKR17373	Sheen	38 ± 3	
	KKR1	Sheen	21 ± 2	
	KKR3	Sheen	16 ± 1	
KKR2	Sheen	12 ± 1		
Application	Robot spray	Quantities		
		gr/m ² min-max:	130 - 160	
	Hand spray	Wet Mils min-max	4,8 - 5,9	
		gr/m ² min-max:	130 - 160	
	Wet Mils min-max	4,8 - 5,9		



PRODUCT PROPERTIES AFTER APPLICATION		
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	12 h
	Dust free	10 min
	Touch dry	40 min
	Hard dry	12 h
	Hot air drying	(Time and temperature according to the drying system in use)
	Shelf life	18 months after production
SPECIFIC WARNINGS	Pastel colors can be obtained by using the converter in combination with KMT10x ColorSeries pigmented pastes up to 10%	



WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products. On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 01/03/2022

Rev.: 3